

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	28	MPa	ISO 527
Yield strain	7	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2.5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	7.5	kJ/m ²	ISO 180/1A
Izod notched impact strength	2.5	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	63	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	53	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, A	151	°C	ISO 306
Vicat softening temperature, B	68	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ISO 1183

Characteristics

Delivery form

Pellets

Special Characteristics

Anti-static, High impact or impact modified

Features

Low Odor, Nucleated, Copolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

Regional Availability

Europe, Asia Pacific, Near East/Africa