

**RTP 305 TFE 15 Z**

(PC+PTFE)-GF30

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	8963	MPa	ASTM D 638
Tensile Strength	114	MPa	ASTM D 638
Flexural Modulus	8618	MPa	ASTM D 790
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	192	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	146	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1550	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	0.02	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	288 - 316	°C	-
Mold temperature	82.2 - 121	°C	-
Injection pressure	68.9 - 103	MPa	-

**Characteristics****Processing**

Injection Molding

**Additives**

Lubricants

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

North America, Europe, Asia Pacific