

EB42P

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	6.4	MPa	ASTM D 638
Izod Impact notched, 1/8 in	343	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	52	J/m	ASTM D 256
Temperature	-30	°C	-

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

Features

Thermal Stability

Applications

Automotive

Regional Availability

Asia Pacific