

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------|-------------------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 6 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 20 | MPa | ISO 527 |
| Flexural modulus, 23°C | 620 | MPa | ISO 178 |
| Shore D hardness | 58 | - | ISO 7619-1 |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 0.45 MPa | 55 | °C | ISO 75-1/-2 |
| Vicat softening temperature, A | 105 | °C | ISO 306 |
| ASTM Data | | | |
| Melting Temperature | 131 | °C | ASTM D 3418 |
| Other properties | | | |
| Density | 895 | kg/m ³ | ISO 1183 |

Characteristics

Additives

Antiblocking agent

Certifications

Food contact

Features

Heat Sealable

Regional Availability

Europe