

**Product Texts**

Coextruded bioriented film.

**Processing/Physical Characteristics**

|                      | Value | Unit    | Test Standard |
|----------------------|-------|---------|---------------|
| <b>ISO Data</b>      |       |         |               |
| Melt flow index, MFI | 5     | g/10min | ISO 1133      |
| Temperature          | 230   | °C      | -             |
| Load                 | 2.16  | kg      | -             |

**Mechanical properties**

|                        | Value | Unit | Test Standard |
|------------------------|-------|------|---------------|
| <b>ISO Data</b>        |       |      |               |
| Yield stress           | 20    | MPa  | ISO 527       |
| Flexural modulus, 23°C | 620   | MPa  | ISO 178       |
| Shore D hardness       | 58    | -    | ISO 7619-1    |

**Thermal properties**

|  | Value | Unit | Test Standard |
|--|-------|------|---------------|
| <b>ISO Data</b>                          |       |      |               |
| Temp. of deflection under load, 0.45 MPa | 55    | °C   | ISO 75-1/-2   |
| Vicat softening temperature, A           | 105   | °C   | ISO 306       |
| <b>ASTM Data</b>                         |       |      |               |
| Melting Temperature                      | 131   | °C   | ASTM D 3418   |

**Other properties**

|         | Value | Unit              | Test Standard |
|---------|-------|-------------------|---------------|
| Density | 895   | kg/m <sup>3</sup> | ISO 1183      |

**Characteristics****Additives**

Antiblocking agent

**Features**

Heat Sealable

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe