

Product Texts

Coextruded bioriented film.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	620	MPa	ISO 178
Shore D hardness	58	-	ISO 7619-1

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
ASTM Data			
Melting Temperature	131	°C	ASTM D 3418

Other properties

	Value	Unit	Test Standard
Density	895	kg/m ³	ISO 1183

Characteristics**Additives**

Antiblocking agent

Features

Heat Sealable

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe