

**Product Texts**

Propylene / alpha olefin copolymer.  
Coextruded bioriented film.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Shore D hardness	58	-	ISO 7619-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	102	°C	ISO 306
<b>ASTM Data</b>			
Melting Temperature	131	°C	ASTM D 3418
<b>Other properties</b>			
Density	895	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Features**

Heat Sealable, Copolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe