

**Product Texts**

Random copolymer with a high ethylene content.  
Coextruded bioriented metallisable film.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>7</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>720</b>	MPa	ISO 178
Shore D hardness	<b>62</b>	-	ISO 7619-1
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>134</b>	°C	ASTM D 3418
<b>Other properties</b>			
Density	<b>895</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Film Extrusion

**Regional Availability**

Europe

**Features**

Heat Sealable, Copolymer, Random Copolymer