

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>0.8</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>1500</b>	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>167</b>	°C	ISO 11357-1/-3

### Characteristics

#### Processing

Injection Molding, Pipe/Tube Extrusion

#### Regional Availability

Europe

#### Features

Nucleated, Thermal Stability, Copolymer, Impact Copolymer