

EP2 X 49 GA

PP

Petrochemical Commercial Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1050	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	136	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Transparent

Regional Availability

Europe, Asia Pacific, Near East/Africa

Applications

Packaging