

RTP 300 TFE 18 SI 2

(PC+PTFE+SI)

RTP Company

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|--------------|-------|---------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.007 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------------|------|---------------|
| ASTM Data | | | |
| Tensile Modulus | 2068 | MPa | ASTM D 638 |
| Tensile Strength | 44.8 | MPa | ASTM D 638 |
| Flexural Modulus | 2206 | MPa | ASTM D 790 |
| Flexural Strength | 71 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 320 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|--------------------|-------------|------|---------------|
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.59 | mm | - |

| Other properties | Value | Unit | Test Standard |
|------------------|-------------|-------------------|---------------|
| Density | 1300 | kg/m ³ | ASTM D 792 |
| Moisture Content | 0.02 | % | - |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|-------------------|------|---------------|
| Pre-drying - Temperature | 121 | °C | - |
| Pre-drying - Time | 4 | h | - |
| Melt temperature | 288 - 316 | °C | - |
| Mold temperature | 82.2 - 121 | °C | - |
| Injection pressure | 68.9 - 103 | MPa | - |

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Additives

Lubricants