

EP-D 60 R

PP

Petrochemical Commercial Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.4	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1050	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	86	°C	ISO 75-1/-2
Vicat softening temperature, A	151	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Blow Molding

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific, Near East/Africa