

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.26	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Yield	14	%	ASTM D 638
Gardner Impact	29.4	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	534	J/m	ASTM D 256

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Blow Molding

Delivery form

Natural Color

Special Characteristics

Heat stabilized or stable to heat, Transparent

Features

Weldable, Copolymer, Random Copolymer

Chemical Resistance

General Chemical Resistance, Hydrolytically Stable

Applications

Chemical Process

Regional Availability

North America, Europe, South and Central America