

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>33.8</b>	MPa	ASTM D 638
Elongation at Yield	<b>10.5</b>	%	ASTM D 638
Izod Impact notched, 1/8 in	<b>45.4</b>	J/m	ASTM D 256

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Features

Homopolymer

#### Applications

General Purpose

#### Regional Availability

North America, Europe, South and Central America