

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	22.7	MPa	ASTM D 638
Elongation at Yield	8.2	%	ASTM D 638
Gardner Impact	31.6	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	240	J/m	ASTM D 256

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

High impact or impact modified

Features

Thermal Stability, Copolymer, Impact Copolymer

Chemical Resistance

General Chemical Resistance

Applications

General Purpose

Regional Availability

North America, Europe, South and Central America