

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 7 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|--------------------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 30.3 | MPa | ASTM D 638 |
| Elongation at Yield | 6.3 | % | ASTM D 638 |
| Gardner Impact | 28.2 | J | ASTM D 2794,4226,5420 |
| Izod Impact notched, 1/8 in | 107 | J/m | ASTM D 256 |

Characteristics

Processing

Injection Molding, Compression Molding

Additives

Release agent

Special Characteristics

Anti-static, High impact or impact modified

Features

Copolymer, Impact Copolymer

Applications

General Purpose

Regional Availability

North America, Europe, South and Central America