

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
Gardner Impact	30.5	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	534	J/m	ASTM D 256

Characteristics

Processing

Injection Molding

Special Characteristics

Anti-static, High impact or impact modified

Features

Nucleated, Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America, Europe, South and Central America