

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	29	MPa	ASTM D 638
Elongation at Yield	9.5	%	ASTM D 638
Izod Impact notched, 1/8 in	39.5	J/m	ASTM D 256

Characteristics

Processing

Coating

Regional Availability

North America, Europe, South and Central America

Features

Good Adhesion, Good Drawdown, Low Neck-In, Copolymer, Impact Copolymer