

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	31	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Rockwell Hardness	R 83	-	ASTM D 785
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	98	°C	ASTM D 648
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Blow Molding, Thermoforming

### Special Characteristics

Transparent

### Features

Copolymer, Random Copolymer

### Chemical Resistance

Oxidation Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Medical

### Regional Availability

North America