

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	32.7	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Rockwell Hardness	100	-	ASTM D 785
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	98.3	°C	ASTM D 648
DTUL @ 264 psi	55	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

Heat stabilized or stable to heat

Features

Thermal Stability, Homopolymer

Applications

General Purpose

Regional Availability

North America