

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	48.3	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	101	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	2.5	%	ASTM D 1003
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Film Extrusion

### Additives

Antiblocking agent

### Features

Homopolymer

### Chemical Resistance

Oxidation Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Regional Availability

North America