

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	430	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	430	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	162	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	162	°C	ASTM D 3418
Other properties			
Density	900	kg/m ³	ISO 1183
Density	900	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

High impact or impact modified

Features

Good Adhesion, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa