

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	24.5	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Gardner Impact	21.8	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	171	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	100	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

High Crystallinity, Low Warpage, Copolymer, Impact Copolymer

Regional Availability

North America, South and Central America