

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	3.9	%	ASTM D 638
Gardner Impact	27.7	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	192	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	96.1	°C	ASTM D 648
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding, Blow Molding

### Delivery form

Pellets, Natural Color

### Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

### Features

High Crystallinity, Nucleated, Copolymer, Impact Copolymer

### Regional Availability

North America