

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	28.5	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Rockwell Hardness	84	-	ASTM D 785
Izod Impact notched, 1/8 in	85.4	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	76.1	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	8.6	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Natural Color

### Special Characteristics

Anti-static, Transparent

### Features

Copolymer, Random Copolymer

### Applications

General Purpose, Medical, Packaging

### Regional Availability

North America