

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	14	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	1100	MPa	ISO 527
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics

Delivery form

Granules, Natural Color

Features

Homopolymer

Applications

Automotive

Regional Availability

Europe