

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	19	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	17	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	13	MPa	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	48	°C	ISO 75-1/-2
Other properties			
Density	980	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Ductile

Applications

Automotive

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa