

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	38	cm ³ /10min	ISO 1133
Melt flow index, MFI	32	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	16.8	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Flexural modulus, 23°C	1670	MPa	ISO 178
Izod notched impact strength	7.5	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Other properties			
Density	1010	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Applications

Automotive

Regional Availability

Europe, Near East/Africa