

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------|------------------------|---------------|
| ISO Data | | | |
| Melt volume-flow rate, MVR | 22 | cm ³ /10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Melt flow index, MFI | 16 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 17 | MPa | ISO 527 |
| Yield strain | 4 | % | ISO 527 |
| Stress at break | 13 | MPa | ISO 527 |
| Flexural modulus, 23°C | 1030 | MPa | ISO 178 |
| Charpy notched impact strength, +23°C | 21 | kJ/m ² | ISO 179/1eA |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 45 | °C | ISO 75-1/-2 |
| Temp. of deflection under load, 0.45 MPa | 69 | °C | ISO 75-1/-2 |
| Other properties | | | |
| Density | 900 | kg/m ³ | ISO 1183 |

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

High impact or impact modified

Features

Scratch Resistant

Applications

Automotive

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa