

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	17	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	25	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	19	MPa	ISO 527
Strain at break	23	%	ISO 527
Charpy notched impact strength, +23°C	4.7	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	1050	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets, Black

#### Features

Creep Resistance, Low Warpage

#### Applications

Automotive

#### Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa