

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	21	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	23.3	MPa	ISO 527
Yield strain	5.1	%	ISO 527
Charpy notched impact strength, +23°C	9.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Other properties			
Density	915	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

High impact or impact modified

Applications

Automotive

Regional Availability

Europe, Near East/Africa