

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	14	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	34	MPa	ISO 527
Yield strain	4.2	%	ISO 527
Charpy notched impact strength, +23°C	2.6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	115	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Special Characteristics

U.V. stabilized or stable to weather

### Applications

Automotive

### Regional Availability

Europe, Near East/Africa