

Globalene 7011

PP

LCY Chemical Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	24.5	MPa	ASTM D 638
Elongation at Yield	15	%	ASTM D 638
Flexural Modulus	981	MPa	ASTM D 790
Rockwell Hardness	R 58	-	ASTM D 785
Izod Impact notched, 1/8 in	814	J/m	ASTM D 256
Other properties			
Density	895	kg/m ³	ASTM D 792

Characteristics**Processing**

Pipe/Tube Extrusion, Sheet Extrusion, Blow Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Asia Pacific