

Globalene PF3006

PP

LCY Chemical Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.015	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	35.1	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1511	MPa	ASTM D 790
Izod Impact notched, 1/8 in	49	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Other properties			
Density	920	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Pellets

Regional Availability

North America, Asia Pacific