

Globalene PT231M

PP

LCY Chemical Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	26	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.013	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	38.3	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Flexural Modulus	1834	MPa	ASTM D 790
Rockwell Hardness	R 104	-	ASTM D 785
Izod Impact notched, 1/8 in	17	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Transparent

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR, US Pharmacopeia Class VI Approved

Regional Availability

North America, Asia Pacific