

Globalene SJ3003

PP

LCY Chemical Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	17	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.014	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.9	MPa	ASTM D 638
Elongation at Yield	6.5	%	ASTM D 638
Flexural Modulus	1236	MPa	ASTM D 790
Rockwell Hardness	R 84	-	ASTM D 785
Izod Impact notched, 1/8 in	75	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94

Other properties	Value	Unit	Test Standard
Density	930	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Pellets

Regional Availability

North America, Asia Pacific