

Gryfilen® C12-N

PP

Grupa Azoty S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	24	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	1320	MPa	ISO 178
Izod notched impact strength, +23°C	12	kJ/m ²	ISO 180/1A

Characteristics**Features**

Nucleated, Copolymer, Impact Copolymer

Regional Availability

Europe