

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>0.35</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	<b>37</b>	MPa	ISO 527
Yield strain	<b>8</b>	%	ISO 527
Flexural modulus, 23°C	<b>1600</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A

## Characteristics

### Processing

Pipe/Tube Extrusion, Sheet Extrusion, Other Extrusion

### Special Characteristics

Heat stabilized or stable to heat

### Features

Homopolymer

### Chemical Resistance

General Chemical Resistance

### Regional Availability

Europe