

**Gryfilen® R08-F**

PP

Grupa Azoty S.A.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>8</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>25</b>	MPa	ISO 527
Yield strain	<b>9</b>	%	ISO 527
Flexural modulus, 23°C	<b>760</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A

**Characteristics****Processing**

Film Extrusion

**Special Characteristics**

Transparent

**Features**

High Gloss, Weldable, Copolymer, Random Copolymer

**Regional Availability**

Europe