

**H 202HC**

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	23	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	41	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Rockwell Hardness	R 109	-	ASTM D 785
Izod Impact notched, 1/8 in	20	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	127	J/m	ASTM D 256
Temperature	-20	°C	-
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Chemical Resistance**

General Chemical Resistance

**Features**

Barrier Properties, Homopolymer

**Regional Availability**

North America, Europe, South and Central America