

**H12G-01**

PP

INEOS Olefins &amp; Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	35.8	MPa	ASTM D 638
Elongation at Yield	9.4	%	ASTM D 638
Elongation at Break	109	%	ASTM D 638
Rockwell Hardness	R 103	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	102	°C	ASTM D 648
Vicat Temperature	153	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	909	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Film Extrusion, Sheet Extrusion

**Features**

Homopolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

General Purpose, Packaging

**Regional Availability**

North America