

H12Z-00

PP

INEOS Olefins & Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	37.5	MPa	ASTM D 638
Tensile Strength at Break	18	MPa	ASTM D 638
Elongation at Yield	8.6	%	ASTM D 638
Elongation at Break	78	%	ASTM D 638
Rockwell Hardness	R 103	-	ASTM D 785
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	120	°C	ASTM D 648
Optical properties			
ASTM Data			
Gloss	92	-	ASTM D 2457
Haze	55	%	ASTM D 1003
Other properties			
Density	912	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

Anti-static

Features

Nucleated, Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America