

HC110BF

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.2	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	161	°C	ISO 11357-1/-3

Characteristics**Processing**

Injection Molding, Film Extrusion, Other Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Barrier Properties, High Crystallinity, High Gloss, Homopolymer

Chemical Resistance

Oil Resistance

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe