

HC117FB

PP

Borouge

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	161	°C	ISO 11357-1/-3
Vicat softening temperature, A	152	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics**Features**

Homopolymer

Certifications

Food contact

Applications

Monofilament

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa