

HF420FB

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	161	°C	ISO 11357-1/-3

Characteristics**Processing**

Fiber Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Homopolymer

Certifications

Food contact

Regional Availability

Europe