

HIVAL® 2435SF

PP

Nexo Plastics, LLC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	1551	MPa	ASTM D 790

Characteristics**Processing**

Injection Molding, Fiber Extrusion

Certifications

Food contact, Food approval FDA 21 CFR

Features

Homopolymer

Regional Availability

North America