

Hifax CA 60 C/M 1750

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	6	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	80	MPa	ISO 178
Thermal properties			
ISO Data			
Vicat softening temperature, A	56	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Soft Feel, Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Regional Availability

North America, Europe, South and Central America