

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	6	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	80	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	56	°C	ISO 306
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Features**

Soft Feel, Copolymer

**Delivery form**

Pellets, Black

**Applications**

Automotive

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Regional Availability**

Europe