

Hifax EP2 015/60M

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	19	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	700	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	148	°C	ISO 11357-1/-3
Vicat softening temperature, A	125	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Coating

Delivery form

Powder

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Good Adhesion, Thermal Stability, Copolymer

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa