

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	5	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	900	MPa	ISO 527
Yield stress	22	MPa	ISO 527
Yield strain	10	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	54	°C	ISO 75-1/-2
Vicat softening temperature, B	56	°C	ISO 306
<b>Other properties</b>			
Density	910	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets, Black

**Applications**

Automotive

**Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe